

PITTARC S3

SCP
SIAT

Descrizione/Description

Filo per saldatura in arco sommerso (SAW) per l'unione di acciaio al carbonio non legati, acciai strutturali, acciai per recipienti a pressione, acciai a grano fine, ecc.

Wire electrode for submerged arc welding (SAW) of non-alloy steels, structural steels, pressure vessels steels, fine-grained steels, etc.

Classificazione/Classification

EN ISO 14171-A S3
AWS A5.17/A5.23 EH10K

Composizione chimica del filo/Wire electrode chemical composition

		C%	Mn%	Si%
PITTARC S3	min	0,07	1,30	0,05
	max	0,15	1,70	0,15
ISO 14171-A-S3	min	0,07	1,30	
	max	0,15	1,75	0,15
AWS A5.17/A5.23-EH10K	min	0,07	1,30	0,05
	max	0,15	1,70	0,25

Approvazioni/Approvals

DB, TÜV.



S.I.A.T. – Società Italiana
Acciai Trafilati S.p.A.
Via Facini, 54
33013 Gemona del Friuli
(Udine) - Italy
Tel.: +39 0432 062 811
Fax: +39 0432 062 960
www.pittarc.com

Per ulteriori informazioni relative al filo S3 vedere la scheda prodotto di riferimento Doc. SPP121.
For further information concerning the wire type S3 refer to the product data sheet Doc. SPP121.

All data/information of this document are only at informative title and not binding for SIAT S.p.A., who entitles full right to modify/change them without prior notice.