



PITTARC



SAW

Unterpulver-Schweissdrähte

Fils arc submergé

Typen Typologie	Klassifizierung Classification	Zulassungen Certifications	Chemische analyse / Analyse chimique							
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S1	ISO 14171-A S1 AWS A5.17 / A5.23 EL12	TÜV - DB	min	0.06	0.35	-	-	-	-	-
			max	0.10	0.60	0.10	0.15	0.15	0.15	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2	ISO 14171-A S2 AWS A5.17 / A5.23 EM12K	TÜV - DB - LRS	min	0.07	1.00	0.10	-	-	-	-
			max	0.15	1.20	0.15	0.15	0.15	0.15	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2Si	ISO 14171-A S2Si AWS A5.17 / A5.23 EM12K	TÜV - DB	min	0.07	0.80	0.15	-	-	-	-
			max	0.15	1.20	0.35	0.15	0.15	0.15	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2Si2	ISO 14171-A S2Si2 AWS A5.17 / A5.23 EM13K	TÜV	min	0.07	0.90	0.40	-	-	-	-
			max	0.15	1.30	0.60	0.10	0.10	0.10	0.20
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S3	ISO 14171-A S3 AWS A5.17 / A5.23 EH10K	TÜV - DB	min	0.07	1.30	0.05	-	-	-	-
			max	0.15	1.70	0.15	0.15	0.15	0.15	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S3Si	ISO 14171-A S3Si AWS A5.17 / A5.23 EH12K	TÜV - DB	min	0.08	1.50	0.20	-	-	-	-
			max	0.12	1.85	0.35	0.15	0.15	0.15	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S4	ISO 14171-A S4 AWS A5.17 / A5.23 EH14	TÜV - DB	min	0.10	1.75	-	-	-	-	-
			max	0.15	2.20	0.10	0.15	0.15	0.15	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2Mo	ISO 14171-A S2Mo ISO 24598-A SMo AWS A5.23 EA2	TÜV - DB	min	0.08	0.95	0.05	-	-	0.45	-
			max	0.15	1.20	0.20	0.15	0.15	0.65	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S3Mo	ISO 14171-A S3Mo AWS A5.23 EA4	TÜV - DB	min	0.08	1.30	0.05	-	-	0.45	-
			max	0.15	1.70	0.20	0.15	0.15	0.65	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S4Mo	ISO 14171-A S4Mo AWS A5.23 EA3	TÜV - DB	min	0.08	1.75	0.05	-	-	0.45	-
			max	0.15	2.15	0.20	0.15	0.15	0.65	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S4MoSi	ISO 14171-A SZ AWS A5.23 EA3K	TÜV	min	0.07	1.70	0.50	-	-	0.40	-
			max	0.12	2.10	0.80	0.15	0.15	0.60	0.25
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
SH2	ISO 14171-A S2Ni1Cu AWS A5.23 EG	TÜV - DB	min	0.08	0.90	0.15	0.65	0.15	-	0.40
			max	0.12	1.10	0.35	0.90	0.40	0.15	0.65
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2Cr1Mo	ISO 24598-A S CrMo1 AWS A5.23 EB2	TÜV	min	0.11	0.85	0.05	-	1.00	0.45	-
			max	0.14	1.00	0.15	0.15	1.30	0.65	0.10
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S1Cr2Mo1	ISO 24598-A S CrMo2 AWS A5.23 EB3	TÜV	min	0.12	0.40	0.05	-	2.35	0.90	-
			max	0.15	0.70	0.25	0.10	2.60	1.05	0.20
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2Ni1	ISO 14171-A S2Ni1 AWS A5.23 ENi1	TÜV	min	0.09	0.80	0.05	0.80	-	-	-
			max	0.12	1.25	0.25	1.20	0.10	0.10	0.20
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2Ni2	ISO 14171-A S2Ni2 AWS A5.23 ENi2	TÜV	min	0.07	0.90	0.05	2.10	-	-	-
			max	0.11	1.15	0.25	2.40	0.10	0.10	0.15
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S2Ni3	ISO 14171-A S2Ni3 AWS A5.23 ENi3	TÜV	min	0.07	0.90	0.05	3.15	-	-	-
			max	0.12	1.15	0.25	3.60	0.10	0.10	0.15
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S3Ni1Mo0,2	ISO 14171-A S3Ni1Mo0,2 AWS A5.23 ENi5	TÜV	min	0.08	1.30	0.15	0.80	-	0.15	-
			max	0.12	1.60	0.30	1.00	0.15	0.30	0.15
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S3Ni1Mo	ISO 26304-A S3Ni1Mo AWS A5.23 EF3	TÜV	min	0.10	1.70	0.05	0.80	-	0.45	-
			max	0.15	1.80	0.25	1.00	0.20	0.65	0.30
			%	C	Mn	Si	Ni	Cr	Mo	Cu*
S3Ni2½CrMo	EN ISO 26304-A S3Ni2,5CrMo AWS A5.23 EG (~AWS A5.23 EM4)	TÜV	min	0.07	1.30	0.10	2.20	0.50	0.40	-
			max	0.10	1.60	0.25	2.60	0.75	0.70	0.15
			%	C	Mn	Si	Mo	Ti	B	Cu*
S3TiB	ISO 14171-A SZ AWS A5.23 EG	TÜV	min	0.06	1.50	0.20	-	0.13	0.009	-
			max	0.10	1.60	0.35	0.05	0.19	0.016	0.10
			%	C	Mn	Si	Mo	Ti	B	Cu*
S3MoTiB	ISO 14171-A S2MoTiB AWS A5.23 EA2TiB	TÜV - DB	min	0.06	1.15	0.20	0.45	0.12	0.010	-
			max	0.08	1.25	0.30	0.60	0.16	0.016	0.12
			%	C	Mn	Si	Mo	Ti	B	Cu*

* Kupfer-Gehalt inklusiv der Verkupferung / Teneur en cuivre, y compris le placage de cuivre